

Primer for Fluoroelastomer Coating DAI-EL LATEX GLP-102NR

 TECHNICAL
DATASHEET

Solvent-based primer for DAI-EL LATEX topcoat.

Introduction

- DAI-EL LATEX GLP-102NR is a solvent-based primer for DAI-EL LATEX topcoat.
- It makes a clear primer layer displaying excellent adhesion to various kinds of elastomer and metal substrate.

Characteristics

Specific gravity of liquid	Drying temperature [°C]	Applicable material	Characteristics	Processing method
0.8	60~80	NBR, IIR etc	Solvent-based (mainly consist of butyl alcohol)	Dipping or Spraying

Characteristics of the coating film

Items	Unit	Data	Reference
Adhesion to			Without primer
NBR	kN/m	1.3	0.5
IIR		0.6	0.4

※Processing condition : Primer · 10 min at 60 to 80°C, DAI-EL LATEX · 30 min at 150°C

※As there may be cases of ineffective adhesion due to specific types and compositions of synthetic rubber, please conduct tests beforehand.

* The numeric values above are typical and not guaranteed.

Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

For more information, visit our website.

DAIKIN INDUSTRIES, LTD.

<https://www.daikinchemicals.com/>

tds-glp-102nr-E_ver01_Mar_2018
Copyright (C) DAIKIN INDUSTRIES, LTD., 2018