

Fluoroelastomer DAI-EL GBR-6002

TECHNICAL DATASHEET

DAI-EL GBR-6002 is a fluoroelastomer which provides excellent resistance to amines and bases with good processability, compression set and resistance to steam and acids.

Introduction

- DAI-EL GBR-6002 is a peroxide curable copolymer of vinylidene fluoride and 2,3,3,3-tetrafluoropropylene, which provides excellent resistance to amines and bases such as engine coolants, lubricating oils, some oil & gas drilling fluids and other high pH environments.
- It offers superior processability, compression set and resistance to steam and acids compared with other base resistant fluoroelastomers.

General physical properties—Product*1

Items	Data	Test method
Color	White to milky white	Visual observation
Fluorine Content	62 mass%	_
Specific Gravity (23°C)	1.72	ASTM D792
Mooney Viscosity (ML ₁₊₁₀)	49 (100°C), 25 (121°C)	ASTM D1646
Solubility	Soluble in lower ketones and esters —	

General physical properties—Vulcanizate*1*2

Items	Units	Numeric Value	Test method
100% Tensile Stress	MPa	1.7	ASTM D412
Tensile Strength	MPa	19.4	ASTM D412
Elongation at Break	%	520	ASTM D412
Communication Soft	0/	27	70hrs@200°C,
Compression Set	%		25% compression*3
Hardness (Shore A)	_	63 (peak), 58 (3sec)	ASTM D2240
Low Temperature Retraction (TR10)	°C	-12	ASTM D1329

^{*1} The above values are representative and not guaranteed.

Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

^{*2 [}Formula] DAI-EL GBR-6002: 100 phr, MT carbon black (N990): 20 phr, Triallylisocyanurate (100% active): 4 phr, 2,5-dimethyl-2,5-di(t-butylperoxy)hexane (100% active): 1.5 phr, [Curing condition] Press cure: 10min@160°C, Post cure: 4hrs@180°C.

^{*3} P-24 O-ring.





Packing specification

- 20kg

For more information, visit our website.

DAIKIN INDUSTRIES,LTD.

https://www.daikinchemicals.com/