

# **Fluoroelastmer DAI-EL G-751**

## **TECHNICAL** DATASHEET

## DAI-EL G-751 is a fluoroelastmer which provides excellent roll mixing processablity and adhesion to metal.

#### Introduction

- DAI-EL G-751 is a cure-incorporated copolymer of vinylidene fluoride and hexafluoropropylene which is \_ suitable for compression molding.
- It provides excellent roll moxing processability and adhesion to metal.

#### General physical properties—Product<sup>\*1</sup>

Items	Data	Test method
Color	Milky white to pale yellow	Visual observation
Fluorine Content	66 mass%	—
Specific Gravity (23°C)	1.81	ASTM D792
Mooney Viscosity (ML <sub>1+10</sub> )	53(100°C), 32(121°C)	ASTM D1646
Solubility	Soluble in lower ketones and esters	—

#### General physical properties—Vulcanizate<sup>\*1\*2</sup>

Items	Units	Numeric Value	Test method	
100% Tensile Stress	MPa	4.9	ASTM D412	
Tensile Strength	MPa	14.6	ASTM D412	
Elongation at Break	%	190	ASTM D412	
Compression Set	%	18	70hrs@200°C,	
			25% compression*3	
Hardness (Shore A)	_	72(peak), 68(3sec)	ASTM D2240	
Low Temperature Retraction (TR10)	°C	-18	ASTM D1329	

<sup>\*1</sup> The above values are representative and not guaranteed.

<sup>\*2</sup> [Formula] DAI-EL G-751: 100 phr, MT carbon black (N990): 20 phr, Calcium hydroxide: 6 phr, Magnesium Oxide (highactive): 3 phr, [Curing condition] Press cure: 10min@170°C, Post cure: 24hrs@230°C.

\*3 P-24 O-ring.

#### Handling / Safety information

- Be sure to read the Safety Data Sheet (SDS) and precautions on the label before using.
- This product has been developed for industrial purposes and we shall not guarantee the safety if used for any other purposes. If it is going to be used for medical or food applications, please contact us in advance.



### **Packing specification**

- 20Kg

For more information, visit our website.

DAIKIN INDUSTRIES, LTD.

https://www.daikinchemicals.com/

tds-g-751-E\_ver01\_Nov\_2019 Copyright (C) DAIKIN INDUSTRIES, LTD., 2019