

Fluoroelastmer DAI-EL G-797

TECHNICAL DATASHEET

DAI-EL G-797 is a fluoroelastmer which has good fluidity of molding and mechanical properties.

Introduction

- DAI-EL G-797 is a cure-incorporated copolymer of vinylidene fluoride and hexafluoropropylene which is suitable for compression molding.
- It provides excellent fluidity of molding and mechanical properties.

General physical properties—Product*1

Items	Data	Test method
Color	Milky white to pale yellow	Visual observation
Fluorine Content	66 mass%	_
Specific Gravity (23°C)	1.81	ASTM D792
Mooney Viscosity (ML ₁₊₁₀)	47(100°C), 25(121°C)	ASTM D1646
Solubility	Soluble in lower ketones and esters —	

General physical properties—Vulcanizate*1*2

notal projectal proportion rationing				
Items	Units	Numeric Value	Test method	
100% Tensile Stress	MPa	3.4	ASTM D412	
Tensile Strength	MPa	15.2	ASTM D412	
Elongation at Break	%	270	ASTM D412	
Compression Set	%	22	70hrs@200°C,	
			25% compression*3	
Hardness (Shore A)		69(peak), 64(3sec)	ASTM D2240	
Low Temperature Retraction (TR10)	°C	-18	ASTM D1329	

^{*1} The above values are representative and not guaranteed.

Handling / Safety information

- Be sure to read the Safety Data Sheet (SDS) and precautions on the label before using.
- This product has been developed for industrial purposes and we shall not guarantee the safety if used for any other purposes. If it is going to be used for medical or food applications, please contact us in advance.

Packing specification

20Kg

For more information, visit our website.

DAIKIN INDUSTRIES, LTD.

https://www.daikinchemicals.com/

^{*2 [}Formula] DAI-EL G-797: 100 phr, MT carbon black (N990): 20 phr, Calcium hydroxide: 6 phr, Magnesium Oxide (highactive): 3 phr, [Curing condition] Press cure: 10min@170°C, Post cure: 24hrs@230°C.

^{*3} P-24 O-ring.