

# Fluoroelastomer DAI-EL G-684BP

 TECHNICAL  
DATASHEET

**DAI-EL G-684BP is a fluoroelastomer which has excellent injection moldability with excellent chemical resistance and good compression set.**

## Introduction

- DAI-EL G-684BP is a bisphenol curable terpolymer of vinylidene fluoride, tetrafluoroethylene and hexafluoropropylene which has excellent **injection moldability**.
- It offers excellent **chemical resistance** and good **compression set**.
- It does not contain curing agent and accelerator.

## General physical properties—Product\*1

Items	Data	Test method
Color	Pale blown	Visual observation
Fluorine Content	70 mass%	—
Specific Gravity (23°C)	1.90	ASTM D792
Mooney Viscosity (ML <sub>1+10</sub> )	81 (100°C), 44 (121°C)	ASTM D1646
Solubility	Soluble in lower ketones and esters	—

\*1 The above values are representative and not guaranteed.

## Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

## Packing specification

- 20kg

For more information, visit our website.

**DAIKIN INDUSTRIES, LTD.**

<https://www.daikinchemicals.com/>