

# Perfluoroelastomer DAI-EL PERFLUOR GA-100

 TECHNICAL  
DATASHEET

## Introduction

- DAI-EL PERFLUOR GA-100 is a peroxide-curable perfluoroelastomer (FFKM) with excellent chemical resistance and cleanliness.
- Due to its high purity, it can be used in highly clean environments such as semiconductor manufacturing processes.

## General physical properties-Product \*1

Items	Value	Test Method
Appearance	Colorless and transparent	Visual Inspection
Mooney Viscosity (ML 1+10@100 °C)	56	JIS K 6300

## General physical properties-Cured \*1.2.3

Items	Units	Value	Test method
Hardness (Shore A)	-	78	JIS K 6253
Tensile Strength at Break	MPa	18.9	JIS K 6251
Elongation at Break	%	160	JIS K 6251
Modulus, 100%	MPa	7.9	JIS K 6251
Compression Set 70h@200 °C, 25% deflection	%	16	JIS K 6262

\*1 The above values are representative and not guaranteed.

\*2 Test compound: DAI-EL PERFLUOR GA-100: 100; N-990 Carbon black: 8;  
N-774 Carbon black: 7; TAIC: 3; 2,5-dimethyl-2,5-di(t-butylperoxy)hexane: 1

\*3 Press cure: 10 min@160 °C; Post cure: 4 hr@180 °C

## Handling and Safety Information

- Be sure to read the Safety Data Sheet (SDS) and take appropriate precautions before use.
- The product is intended for industrial use only and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

## Package

- 2 kg, 10 kg

For more information, visit our website.  
**DAIKIN INDUSTRIES, LTD.**

<https://www.daikinchemicals.com/>

[tds-ga-100-E\\_ver01\\_Jun\\_2026](#)

Copyright (C) DAIKIN INDUSTRIES, LTD., 2026