

Fluoroelastomer DAI-EL G-9074

 TECHNICAL
DATASHEET

DAI-EL G-9074 is a fluoroelastomer which provides excellent compression set and resistance to steam and acids.

Introduction

- DAI-EL G-9074 is a peroxide curable terpolymer of vinylidene fluoride, tetrafluoroethylene and hexafluoropropylene which has excellent **mold flow**. It is suitable for injection molding.
- It provides excellent **compression set** and **resistance to steam and acids**. It has highest fluorine content of all grades, which provides excellent **chemical resistance**.

General physical properties—Product*1

Items	Data	Test method
Color	Translucent to pale yellow	Visual observation
Fluorine Content	70.5 mass%	—
Specific Gravity (23°C)	1.91	ASTM D792
Mooney Viscosity (ML ₁₊₁₀)	66 (100°C), 42 (121°C)	ASTM D1646
Solubility	Soluble in lower ketones and esters	—

General physical properties—Vulcanizate*1*2

Items	Units	Numeric Value	Test method
100% Tensile Stress	MPa	3.6	ASTM D412
Tensile Strength	MPa	18.5	ASTM D412
Elongation at Break	%	260	ASTM D412
Compression Set	%	18	70hrs@200°C, 25% compression ^{*3}
Hardness (Shore A)	—	71 (peak), 65 (3sec)	ASTM D2240
Low Temperature Retraction (TR10)	°C	-6	ASTM D1329

*1 The above values are representative and not guaranteed.

*2 [Formula] DAI-EL G-9074: 100 phr, MT carbon black (N990): 20 phr, Triallylisocyanurate (100% active): 4 phr, 2,5-dimethyl-2,5-di(t-butylperoxy)hexane (100% active): 1.5 phr, [Curing condition] Press cure: 10min@160°C, Post cure: 4hrs@180°C.

*3 P-24 O-ring.

Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

Packing specification

- 20kg

For more information, visit our website.

DAIKIN INDUSTRIES, LTD.

<https://www.daikinchemicals.com/>

tds-g-9074-E_ver01_Apr_2018
Copyright (C) DAIKIN INDUSTRIES, LTD., 2018