

# **Fluoroelastomer DAI-EL G-962**

**TECHNICAL DATASHEET** 

DAI-EL G-962 is a fluoroelastomer which provides excellent mechanical properties and resistance to steam and acids with good low temperature flexibility.

#### Introduction

- DAI-EL G-962 is a peroxide curable terpolymer of vinylidene fluoride, tetrafluoroethylene and hexafluoropropylene which is suitable for injection molding.
- It provides excellent mechanical properties and resistance to steam and acids and a good balance of chemical resistance and low temperature flexibility.

## General physical properties—Product\*1

1,	D. (c.		
Items	Data	Test method	
Color	Translucent to pale pink	Visual observation	
Fluorine Content	67 mass%	_	
Specific Gravity (23°C)	1.83	ASTM D792	
Mooney Viscosity (ML <sub>1+10</sub> )	47 (100°C), 27 (121°C)	ASTM D1646	
Solubility	Soluble in lower ketones and esters	_	

# General physical properties—Vulcanizate\*1\*2

Items	Units	Numeric Value	Test method
100% Tensile Stress	MPa	2.6	ASTM D412
Tensile Strength	MPa	18.0	ASTM D412
Elongation at Break	%	280	ASTM D412
Compression Set	%	17	70hrs@200°C,
Compression Set			25% compression*3
Hardness (Shore A)	_	65 (peak), 63 (3sec)	ASTM D2240
Low Temperature Retraction (TR10)	°C	-19	ASTM D1329

<sup>\*1</sup> The above values are representative and not guaranteed.

### Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

1

<sup>\*2 [</sup>Formula] DAI-EL G-962: 100 phr, MT carbon black (N990): 20 phr, Triallylisocyanurate (100% active): 4 phr,

<sup>2,5-</sup>dimethyl-2,5-di(t-butylperoxy)hexane (100% active): 1.5 phr, [Curing condition] Press cure: 10min@160°C, Post cure: 4hrs@180°C.

<sup>\*3</sup> P-24 O-ring.





# **Packing specification**

- 20kg

For more information, visit our website.

DAIKIN INDUSTRIES,LTD.

https://www.daikinchemicals.com/