

Fluoropolymer Coating Powder **NEOFLON PFA** AC-5600

TECHNICAL DATASHEET

PFA powder for excellent corrosion resistance.

Introduction

- NEOFLON PFA AC-5600 is a PFA powder for electrostatic spraying.
- It makes a clear layers displaying excellent non-stick property and heat resistance.
- It is good for linings in chemical industry.

Characteristics

Film appearance	Processing method	Applicable film thickness	
Clear	Electrostatic	100∼300µm	
	coating		

Physical properties of the powder

Items	Unit	Data	Method of measurement
Bulk density	g/ml	0.6	JIS K6891
Average particle size	μm	50	Laser diffraction
Melting point of raw material	°C	305	ASTM D3307
MFR of raw material	g/10min	6	ASTM D3307

Physical properties of the coating film

Items	Unit	Data	Method of measurement
Friction		0.05 – 0.08	Bauden leben steel sheet
coefficient	-	0.05 – 0.06	badderi leberi steel sileet
Contact angle		400 400	
(Water)	degree	102 – 106	Contact angle meter at
(Hexadecane)		65	25°C
Tensile strength	MPa	19.6 – 31.4	JIS K6888
Elongation	%	250 – 350	JIS K6888

^{*} The numeric values above are typical and not guaranteed.

1



Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

For more information, visit our website.

DAIKIN INDUSTRIES, LTD.

https://www.daikinchemicals.com/