

# Solvent-based Fluoropolymer coating NEOFLON PFA TC-7609M1

## **TECHNICAL** DATASHEET

## Solvent-based PFA coating for non-stick property.

#### Introduction

- NEOFLON PFF TC-7600 grade is a solvent-based PFA coating. \_
- NEOFLON PFA TC-7609M1 makes a black metallic coating layer displaying non-stick property and \_ heat resistance.
- It is good for cooking appliances and kitchen appliances. \_

#### **Characteristics**

Film appearance	Solid content [mass%]	Specific gravity of coating	Viscosity (Ford Cup #4) (sec.)(25°C)
Black metallic	25	1.04	27

#### Characteristics of the coating film

Items	Unit	Data	Method of measurement
Maximum temperature	°C	250	
Wear resistance	mg/1000	mg/1000 rounds 30 - 50	CS-17、1kgf、1000 rounds
Taber abrasion(25°C)	rounds		
Friction coefficient		0.04 - 0.08	Bauden leben type, Steel ball 8mmφ, Linear velocity
			0.27cm/s, Loading 1.0kg
Pencil hardness			
(25°C)		H – 2H	Mitsubishi Uni
(After immersed in			
boiled water for 500h)		H – 2H	
(After immersed in lard			
oil at 260°C for 24h)		F – H	
Contact angle	degree		Contact angle meter at
(Water)	degree	106 - 110	25°C
Chemical resistance			
Sulfuric acid		No change	
Hydrochloric acid		No change	
Nitric acid		No change	for 16h at 25°C
Sodium hydroxide		No change	
Xylene		No change	
Methanol		No change	

\* The numeric values above are typical and not guaranteed.



#### Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

For more information, visit our website.

# DAIKIN INDUSTRIES, LTD.

https://www.daikinchemicals.com/

tds-tc-7609m1-E\_ver01\_Mar\_2018 Copyright (C) DAIKIN INDUSTRIES, LTD., 2018