

Water-based Fluoropolymer Coating **NEOFLON PFA** AD-2CRER

TECHNICAL DATASHEET

Water-based PFA topcoat for non-stick property.

Introduction

- NEOFLON PFA AD-2 grade is a water-based PFA topcoat. _
- NEOFLON PFA AD-2CRER makes a clear topcoat layer displaying non-stick property.
- It makes a pinhole-free film.

Characteristics

| Film appearance | Viscosity [cP] | рН | Solid content [mass%] |
|--------------------|----------------|----|--------------------------|
| Clear | 220 | 9 | 50 |

Physical properties of the coating film

| Items | Unit | Data | Method of measurement 🛛 💥 |
|-----------------------|--------|-----------|----------------------------------|
| Pencil hardness | | | JIS K6894 |
| (25°C) | | H – 3H | (Stripping hardness of base |
| | | | material) |
| Cross-cut adhesion | | | JIS K5400 8.5 |
| | | 100/100 | (Stripping with cellophane tape, |
| | | | 10 times) |
| Contact angle (Water) | | | |
| (Hexadecane) | degree | 110 – 116 | Contact angle meter at 25°C |
| | | 50 – 56 | |

* The coating film was evaluated with a test piece below. Substrate: Aluminum plate roughened with Tosa Emely Extra #80/#100=50/50

Primer: EK-1909S21R, approximately 10µm thick

Topcoat: Approximately 10~15µm thick

* The numeric values above are typical and not guaranteed.

Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

For more information, visit our website.

DAIKIN INDUSTRIES, LTD.

https://www.daikinchemicals.com/