

Water-based Fluoropolymer Coating POLYFLON PTFE EK-3783S21R

 TECHNICAL
DATASHEET

Water-based PTFE topcoat for non-stick property.

Introduction

- POLYFLON PTFE EK-3700 grade is a water-based PTFE topcoat.
- POLYFLON PTFE EK-3783S21R makes a brown topcoat layer displaying non-stick property.
- It is good for cooking appliances and kitchen appliances.

General physical properties

Film appearance	Viscosity [cP]	pH	Solid content [mass%]	Specific gravity of coating
Brown	300	9	41	1.3~1.4

Physical properties of the coating film

Items	Unit	Data	Method of measurement ※ 1
Gloss		15 – 25	JIS K5400 7.6
Pencil hardness (25°C) (200°C)		H – 2H B - HB	JIS K6894 (Stripping hardness of base material)
Cross-cut adhesion		100/100	JIS K5400 8.5 (Stripping with cellophane tape, 10 times)
Taber abrasion (25°C)	mg/1000 rounds	6 – 12	CS-17、1kg、1000 rounds
Boiled water resistance		Good	for 100 hours at 90~95°C
Salt spray		Good	JIS Z2371
Hot oil resistance		Good	for 16 hours at 260°C
Corrosion resistance		Good	Corrosion resistance test ※ 2

※ 1 The coating film was evaluated with a test piece below.

Substrate: Aluminum plate roughened with Tosa Emely Extra #80/#100=50/50

Primer: EK-1909S21R, approximately 10μm thick

Topcoat: Approximately 20μm thick

※ 2 Corrosion resistance test (Oden soup stock test) : 5 cycles of the following; SB Oden soup stock is

dissolved into 1L water and boiled for 1 hour Hot insulation for 7 hours Left unattended for 16 hours

* The numeric values above are typical and not guaranteed.

Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

For more information, visit our website.

DAIKIN INDUSTRIES, LTD.

<https://www.daikinchemicals.com/>

tds-ek-3783s21r-E_ver01_Mar_2018
Copyright (C) DAIKIN INDUSTRIES, LTD., 2018