

Fluoropolymer NEOFLON PFA AP-201

TECHNICAL DATASHEET

NEOFLON PFA AP-201 is a high flowability fluororesin. It is suitable for injection molding of complicated shape products and extrusion molding of thin wall electric wire.

Introduction

- AP-201 is a copolymer of tetrafluoroethylene and perfluoroalkyl vinyl ether.
- Good melt flowability while maintaining excellent properties of PTFE. It can be melt-molded as a thermoplastic resin by injection molding and extrusion molding.
- Suitable for injection molding of complicated shape products and extrusion molding of thin-walled electric wires.
- Excellent chemical resistance which is not affected by most of the chemicals.
- It retains flexibility without losing toughness under the environment from cryogenic to high temperature.
- Low dielectric constant and dielectric loss tangent in a wide range of temperature and frequency.
- It shows high electrical resistance and dielectric strength.
- Nonflammable like POLYFLON PTFE and NEOFLON FEP.
- Excellent weather resistance. No properties change even when exposed outside for a long time.
- Non-stickiness. It shows excellent releasability and water repellency / oil repellency.

General physical properties

Item	Unit	Value	Test Method
MFR	g/10min	28	372°C、5kgf
Melting Point	°C	303	DSC
Specific Gravity	-	2.15	ASTM D 792 Compliant
Tensile Strength	MPa	32	ASTM D 1708 Compliant
Elongation	%	405	ASTM D 1708 Compliant

^{*} The above values are representative values, not guaranteed values.

Handling method / Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.





Packing specification

25Kg

For more information, visit our website.

DAIKIN INDUSTRIES,LTD.

https://www.daikinchemicals.com/